

IN THE SPECIFICATION

Please replace the paragraph bridging pages 19 and 20 as follows:

The cast slabs from example 1 were granulated and injection molded to give 2 mm thick sheets. S 2 test specimens were punched out of these injection-molded sheets. These test specimens were aged in an oven at 130°C. The test specimens were removed from the oven at predefined intervals and tested according to DIN 53504. The Figure [[1]] shows the curve for the elongation at break for the samples according to examples 1.1 to 1.8. It is clear that the addition of metal deactivators improves the stability of the TPU. Moreover, it is found that the preferred metal deactivators from experiments 1.1 and 1.2 have a particularly good effect.